

ADDITOL® VXW 6374

TYPE

Ionic and nonionic surfactant with pigment affinity groups for organic and inorganic pigments in waterborne coating systems

It is free of nonylphenolethoxylates and VOC.

FORM OF DELIVERY (f.o.d.)

Appearance

low-viscous liquid

PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219
dynamic viscosity [mPa.s] 50 - 300
(25 1/s; 23 °C)

pH-Value DIN ISO 976
pH-value 8 - 10
(5 %)

Non-Volatile Matter DIN 55671
non-volatile matter [%] 48 - 52
(150 °C; 10 min)

Colour / Appearance VLN 250
colour yellow

Not continually determined:

Density (Liquids) DIN EN ISO 2811-2
density [g/cm³] 1,04
approx.
(20 °C)

Flash Point (Pensky-Martens) DIN EN ISO 2719
flash point [°C] > 100

SPECIAL PROPERTIES

Additol VXW 6374 effectively improves wetting of organic and inorganic pigments in all aqueous coating systems.

Additol VXW 6374 reduces the grind viscosity and prevents pigment reflocculation during formulated paint storage.

SUGGESTED USES

Additol VXW 6374 is a suitable wetting agent for neutral as well as amine neutralized waterborne coatings systems. It is highly effective for alkyd resin emulsions, acrylics, polyesters, epoxies, UV curing backbone resin systems, polyurethane emulsions as well as standard emulsions designed to formulate quality coating systems.

Additol VXW 6374 is also suited for the preparation of pigment pastes containing no binders.

PROCESSING

Additol VXW 6374 must be milled together with the pigments. It is recommended to add Additol VXW 6374 to the resin base prior to adding the pigments.

The recommended dosage on pigment is:
for inorganic pigments 1.0 - 10.0 %
for organic pigments 10.0 - 40.0 %.

The optimum dosage is related to the entire system mix and should be determined by careful laboratory evaluation.

Foam generation in the milling base can be prevented by using suitable defoamers such as Additol VXW 6356, Additol VXW 6210, Additol VXW 4973 or Additol VXW 4926. Blends of Additol XW 390 or Additol VXW 4971 promotes better flow avoiding surface defects.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

5.0/30.03.2017 (replaces 4.0/17.09.2013)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.