

# ADDITOL® XL 203

## TYPE

Silicone-containing cationic antifoaming, wetting and dispersing agent

## FORM OF DELIVERY (f.o.d.)

Active substance

approx. 40 %

## PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219 dynamic viscosity (100 1/s; 23 °C)	[mPa.s]	30 - 120
--	---------	----------

Iodine Colour Number DIN 6162 iodine colour number		<= 20
---	--	-------

Non-Volatile Matter DIN EN ISO 3251 non-volatile matter (1 h; 125 °C; 1 g)	[%]	38,5 - 41,5
--	-----	-------------

Not continually determined:

Density (Liquids) DIN EN ISO 2811-2 density approx. (20 °C)	[g/cm³]	0,98
--	---------	------

Flash Point DIN EN ISO 1523 flash point approx.	[°C]	63
---	------	----

Appearance

brown, clear liquid

## SPECIAL PROPERTIES

High pigment loading without increase in viscosity.  
Reduction of dispersing time.  
Enhances gloss and levelling.

For air drying and stoving solvent-borne paints and particularly for water dilutable paint systems.

## SUGGESTED USES

Additol XL 203 prevents the floating of titanium dioxide in conjunction with organic or inorganic coloured pigments. It can be employed in solvent-borne and water dilutable air drying and stoving paint systems. Additol XL 203 enhances gloss and levelling of paint films. Pigment loading of paints and pigment pastes can be increased without rises in viscosity. Dispersion time is reduced.

The recommended level may range from 0.1 to 1.5 % on total paint. Level on pigments: inorganic pigments: 0.5 - 2.5 %, organic pigments: 1.5 - 5 %.

The figures given here may serve as a guide for extensive trials to find the optimum in dosage and effect and to save costs. Since Additol XL 203 is a cationic product it should not be used in conjunction with certain anionic products. Phase separation occurs and Additol XL 203 becomes ineffective at once. The compatibility should be determined by experiments. Additol XL 203 can be combined with cationic and non-ionic products.

## PROCESSING

Additol XL 203 should be milled together with the pigments in order to obtain the full effect.

## STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

## DISTINGUISHING FEATURES

In difference to Additol XL 204, Additol XL 203 is a cationic-active antifoaming agent and can be used in solvent- and waterborne paint systems. It is not recommended for acid curing paints.

5.0/30.03.2017 ( replaces 4.0/17.09.2013 )

• Worldwide Contact Info: [www.allnex.com](http://www.allnex.com) •

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or \* are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.