

ADDITOL® XL 204

TYPE

Silicone-containing anion-active antifoaming, wetting and dispersing agent

FORM OF DELIVERY (f.o.d.)

Active substance

approx. 55 %

SPECIAL PROPERTIES

High pigment loading without increase in viscosity.

Reduction of dispersing time.

For air drying and stoving solvent-borne paints and for water dilutable paint systems.

PRODUCT DATA

Determined per batch:

Non-Volatile Matter DIN EN ISO 3251 non-volatile matter *	[%]	47 - 49
---	-----	---------

(1 h; 125 °C; 1 g)

Not continually determined:

Colour / Appearance VLN 250 colour appearance		brown clear
---	--	----------------

Density (Liquids) DIN EN ISO 2811-2 density approx. (20 °C)	[g/cm ³]	0,95
--	----------------------	------

Flash Point DIN EN ISO 1523 flash point approx.	[°C]	17
---	------	----

SUGGESTED USES

Additol XL 204 prevents the floating of titanium dioxide in conjunction with organic or inorganic coloured pigments. It can be employed in solvent-borne and water dilutable air drying and stoving paint systems. Additol XL 204 affords higher pigment loading of the paint system and pigment pastes without causing the viscosity rise usual with such products and, at the same time, reduces dispersing time.

The recommended level may range from 0.1 to 1.5 % on total paint. Level on pigments:

inorganic pigments: 0.5 - 2.5 %

organic pigments: 1.5 - 5.0 %

Levels of addition in water dilutable air drying and stoving system may range from 1 to 6 % on pigments.

The figures given here may serve as a guide for extensive trials to find the optimum in dosage and effect to save costs.

PROCESSING

Additol XL 204 should be milled together with the pigments in order to obtain the full effect.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

DISTINGUISHING FEATURES

In difference to Additol XL 203, Additol XL 204 is an anion-active antifoaming agent and can be used in solvent- and water-borne paint systems. It is not recommended for acid curing paints.

* Note

The non-volatile matter content of a product is not an absolute quantity but depends upon the temperature and period of heating used for the test. Consequently, when using this method, only relative and not true values for non-volatile matter content are obtained owing to solvent retention, thermal decomposition and evaporation of low molecular mass constituents. The method is therefore primarily intended for testing different batches of the same type of product.

DIN EN ISO 3251 (09/95, page 2)

5.0/30.03.2017 (replaces 4.0/17.09.2013)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.