

ADDITOL[®] XL 270

TYPE

Electroneutral wetting and antisetling agent

FORM OF DELIVERY (f.o.d.)

low-viscous liquid

Active substance

approx. 55 %

PRODUCT DATA

Determined per batch:

Iodine Colour Number DIN 6162
iodine colour number <= 18

Non-Volatile Matter DIN 55671
non-volatile matter [%] 43 - 46
(150 °C; 10 min)

Not continually determined:

Non-Volatile Matter DIN EN ISO 3251
non-volatile matter [%] 43 - 46
*
(1 h; 125 °C; 1 g)

Colour / Appearance VLN 250
colour brown
appearance clear

Density (Liquids) DIN EN ISO 2811-2
density [g/cm³] 0,91
approx.
(20 °C)

Flash Point DIN EN ISO 1523
flash point [°C] 26
approx.

SPECIAL PROPERTIES

Prevents the sedimentation of pigments in paints. Improves the pigment-wetting during dispersion. In many paint systems the floating of pigments in pigment-mixtures is prevented. The tendency to flow off is reduced and the covering of edges is improved. Suggested for all solvent based and solvent-free paint systems.

SUGGESTED USES

Additol XL 270 is usually compatible with solvent based and solvent-free binders. It prevents the sedimentation of pigments in paints. The rheological character of paints is improved. The tendency to flow on vertical surfaces is reduced. The edges of substrates are better covered in case of dipping application.

The drying of oxidatively drying systems is not influenced by Additol XL 270, if the appropriated dose is used. Also the efficiency of siccatives in paints, stored for a long time, is not reduced using Additol XL 270.

Considering anti-corrosive paints, there is no corrosion-resistance loss by using Additol XL 270. It is recommended to be used for the activating of organophile bentonites and it improves the effect of pyrogene silica.

PROCESSING

Additol XL 270 can be added in any stage of the paint production. We especially recommend the addition during pigment dispersion.

Amounts of 0.1 - 2.0 % on pigments and fillers may serve as a guide. These are standard values, the most effective dose must be found by experiments.

Standard formulation for the activation of bentonite:

80 - 87 parts xylene or white spirit

10 parts bentonite

10 - 3 parts Additol XL 270

100 parts

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

A slight turbidity of Additol XL 270 is possible, which however does not negatively influence the quality of the paints produced with Additol XL 270.

* Note

The non-volatile matter content of a product is not an absolute quantity but depends upon the temperature and period of heating used for the test. Consequently, when using this method, only relative and not true values for non-volatile matter content are obtained owing to solvent retention, thermal decomposition and evaporation of low molecular mass constituents. The method is therefore primarily intended for testing different batches of the same type of product.

DIN EN ISO 3251 (09/95, page 2)

5.0/30.03.2017 (replaces 4.0/17.09.2013)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.