

# ADDITOL<sup>®</sup> XW 376

## TYPE

Defoamer for waterborne emulsion paints and adhesives and synthetic resin-bound renderings

## FORM OF DELIVERY (f.o.d.)

Active substance  
approx. 50 %

## PRODUCT DATA

Determined per batch:

|  |         |           |
|--|---------|-----------|
| Dynamic Viscosity DIN EN ISO 3219<br>dynamic viscosity<br>(100 1/s; 23 °C) | [mPa.s] | 100 - 300 |
|--|---------|-----------|

Not continually determined:

|   |  |                  |
|---|--|------------------|
| Colour / Appearance VLN 250<br>colour<br>appearance |  | yellow<br>opaque |
|---|--|------------------|

|  |                      |      |
|--|----------------------|------|
| Density (Liquids) DIN EN ISO 2811-2<br>density<br>approx.<br>(20 °C) | [g/cm <sup>3</sup> ] | 0,94 |
|--|----------------------|------|

|   |      |       |
|---|------|-------|
| Flash Point (Pensky-Martens) DIN EN ISO 2719<br>flash point | [°C] | > 100 |
|---|------|-------|

## SPECIAL PROPERTIES

Can be used in most waterborne emulsion paints and adhesives, and in synthetic resin-bound renderings.  
Good storage stability even at elevated temperatures.

## SUGGESTED USES

Additol XW 376 is effective in large to fine particle size dispersions based on polyvinyl acetate, PVC, acrylates and their copolymers as well as alkyd resin emulsions.

It is easily emulsified and also incorporated in low viscosity systems. Additol XW 376 is equally useful in deaeration during pigment grinding and in the filling process; it is shear stable and alkali resistant up to pH = 13.

## PROCESSING

We recommend the addition of 0.05 - 0.5 % Additol XW 376, calculated on finished paint.

In the case of incorporation in low-viscosity products the Additol XW 376 must be well stirred in. The optimum effect of the defoamer should be determined by preliminary trials in the system to be used.

## STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 365 days.

At temperatures below - 10 °C Additol XW 376 can freeze to a solid mass. After thawing Additol XW 376 is ready for use again.

## DISTINGUISHING FEATURES

Additol XW 376 is pre-emulsified and therefore it can be more easily distributed in low-viscosity systems than Additol XW 375 and Additol XW 372.

5.0/30.03.2017 ( replaces 4.0/17.09.2013 )

• Worldwide Contact Info: [www.allnex.com](http://www.allnex.com) •

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or \* are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.