

Revised 5/25/2017

Product Name:	SUPER SEATONE	Burnt Umber	
Code Number:	11B632		
Vehicle Type:	Surfactant Blend		
Solvent:	Water / Propylene Glycol		
Color Index Name:	Br-7		
Suggested for Industrial Finishes ?	Yes		
Product Line Description:	Aqueous pigment dispersions for in-plant tinting of Industrial and Architectural Coatings Super Seatone® aqueous dispersions are designed to be easy to use, free flowing, viscosity stable pigment concentrates. They are tightly controlled for consistent color characteristics when added by weight.		
TYPICAL PROPERTIES	CHEMICAL RESISTANCE		
Lbs/gal	11.2	(1= Poor, 5 = Excellent)	
Wt % Pigment	35.0	Aliphatic	5
Vol % Pigment	13.5	Aromatic	5
Wt % Vehicle Solids	9.5	Ketone Ethyl Acetate	5 5

Vol % Vehicle Solids	12.0	
	12.0	Ethyl Alcohol 5
Wt % Volatile	55.5	Cellosolve 5
Vol % Volatile	74.5	DB Phthalate 5
VOC g/l *	148	Glycol 5
VOC lb/gal *	1.2	Dilute Acid 5
% Propylene Glycol by Wt.	3 .0	Dilute Alkali 5
% Propylene Glycol by Vol.	4.0	Soap 5
EXTERIOR DURABILITY		HEAT RESISTANCE
(1= Poor, 5 = Excellent)		(1= Poor, 5 = Excellent)
MASSTONE	5	150 C - 15' 5
TINT	5	150 C - 30' 5

* Note - For aqueous products, VOC is calculated minus water.

DyStar Hilton Davis 2235 Langdon Farm Rd. Chininnati, OH 45237 USA +1 800-477-1022 +1 513 441 3771 Telephone Fax (marketing) DyStar-USA@DyStar.com www.DyStar.com

This information and our technical advice - whether verbal, in writ-ing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are in-volved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and pro-cessing of our products and the products manufactured by you on the basic of our torbingle advice or baypend our control and, there the basis of our technical advice are beyond our control and, there-fore, entirely your own responsibility. Our products are sold in ac-cordance with our General Conditions of Sale and Delivery.