

# 25-1475 (AEKYUNG AH-4075BX) ALIPHATIC POLYISOCYANATE

## TECHNICAL DATA SHEET

### APPLICATIONS

Wood  
Metal  
Plastic  
Automotive Repair  
Synthetic Leather  
Adhesives  
Heavy Duty Protective Coatings

### DESCRIPTION

25-1475 is a HDI biuret. It is supplied at 75% solids in n-Butyl Acetate and Xylene.

### SOLUBILITY AND COMPATIBILITY

Will generally mix with ketones, esters and aromatic hydrocarbons. Reduction should not be lower than 40% nvm, as this may cause sedimentation or turbidity, when stored for extended periods.

### KEY BENEFITS

Weather Resistance  
High NCO Content  
Flexibility

### TYPICAL PROPERTIES

% Solids	74 -76
Viscosity @ 25°C (cps)	125 – 200
Color (Hazen)	40 APHA
% NCO Content	16.2 - 16.8
% Free Monomer	0.5 maximum
Weight Per Gallon @ 25°C	9.2
Equivalent Weight	255