

ADDITOL® VXW 4926

TYPE

Antifoaming additive for water dilutable paints, without silicone addition

FORM OF DELIVERY (f.o.d.)

Active substance

approx. 100 %

PRODUCT DATA

Determined per batch:

Colour / Appearance VLN 250

colour	yellow
appearance	clear

Dynamic Viscosity DIN EN ISO 3219

dynamic viscosity	[mPa.s]	80 - 200
-------------------	---------	----------

(25 1/s; 23 °C)

Non-Volatile Matter DIN EN ISO 3251

non-volatile matter	[%]	98 - 100
---------------------	-----	----------

(1 h; 125 °C; 1 g)

Not continually determined:

Refractive Index DIN 53491

refractive index		1,479 - 1,482
------------------	--	---------------

(20 °C)

Density (Liquids) DIN EN ISO 2811-2

density	[g/cm ³]	0,95
---------	----------------------	------

approx.
(20 °C)

Flash Point (Pensky-Martens) DIN EN ISO 2719

flash point	[°C]	> 100
-------------	------	-------

SPECIAL PROPERTIES

Rapid defoaming or air release.

Allows high film thickness of stoving paints, without cissing. Also suited for combinations of dispersions with water dilutable synthetic resins.

SUGGESTED USES

Additol VXW 4926 is a surface active additive for water dilutable paints. Particularly with spray application cissing on curing of the paint is prevented or may appear only with higher film thickness.

Since Additol VXW 4926 is not dilutable with water, it should be incorporated with great care.

The dosed range is between 2 % and 15 % for 100 % binder solids. The optimum quantity should be determined in individual tests.

PROCESSING

Since Additol VXW 4926 is not dilutable with water, it must be incorporated with great care.

For testing the optimum dosage, it may be admixed to the finished paint.

However an incorporation together with the pigments and extenders should be aimed at.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

At temperatures below 15 °C turbidity appears, at very low temperatures the product thickens. Therefore Additol VXW 4926 should be stored at temperatures above 15 °C. After storing for 24 hours at room temperature the turbid material liquefies again, a clear solution results, the properties are not injured by this process.

6.0/30.03.2017 (replaces 5.0/17.09.2013)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.