

ADDITOL® VXW 6214

TYPE

Fluorine modified levelling agent and substrate wetting agent for waterborne paint systems, without silicone addition

FORM OF DELIVERY (f.o.d.)

Active substance
approx. 57 %

PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219 dynamic viscosity (25 1/s; 23 °C)	[mPa.s]	1000 - 3500
---	---------	-------------

pH-Value DIN ISO 976 pH-value (10 %)		8,0 - 9,5
--	--	-----------

Non-Volatile Matter DIN 55671 non-volatile matter (120 °C; 10 min)	[%]	48 - 52
--	-----	---------

Not continually determined:

Colour / Appearance VLN 250 colour appearance		pale yellow clear
---	--	----------------------

Non-Volatile Matter DIN EN ISO 3251 non-volatile matter * (1 h; 125 °C; 1 g)	[%]	48 - 52
---	-----	---------

Density (Liquids) DIN EN ISO 2811-2 density approx. (20 °C)	[g/cm³]	1,06
--	---------	------

Flash Point DIN EN ISO 1523 flash point approx.	[°C]	46
---	------	----

SPECIAL PROPERTIES

Additol VXW 6214 prevents in all waterborne paint systems levelling disturbances and promotes due to its excellent wetting effect the spreading performance of the paint on all substrates.

SUGGESTED USES

Additol VXW 6214 may be used in all air and stove drying waterborne paint systems.

Film disturbances during applying by roller coater, spraying and dipping, like craters, defective levelling and variable wetting of the substrate are effectively prevented by Additol VXW 6214.

Based on its reactive groups Additol VXW 6214 is in baking paints incorporated into the paint film and does not impair the recoatability and intercoat adhesion.

PROCESSING

Additol VXW 6214 can be added at any stage of the paint production, preferably however during the pigment dispersing.

Added quantities: 0.2 - 1.0 %, calculated on solid binder.
The most favourable quantity should always be determined in pretrials.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

The colour of Additol VXW 6214 may during storage get darker. However the effectiveness is not impaired.

DISTINGUISHING FEATURES

Additol VXW 6214 is, in comparison to Additol XW 390 and Additol XW 395, especially well suited for externally emulsified waterborne alkyd resin emulsion paints and distinguishes itself by a better substrate wetting.

During production of waterborne paints on the basis of externally emulsified alkyd resin emulsions Additol VXW 6214 exhibits a better wetting effect than Additol XW 390 and Additol XW 395. It is also a better wetting agent for the substrate.

* Note

The non-volatile matter content of a product is not absolute quantity but depends upon the temperature and period of heating used for the test. Consequently, when using this method, only relative and not true values for non-volatile matter content are obtained owing to solvent retention, thermal decomposition and evaporation of low molecular mass constituents. The method is therefore primarily intended for testing different batches of the same type of product.
(DIN EN ISO 3251, 9/95, page 2)

4.0/17.07.2013 (replaces all previous versions)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies (*Allnex*) decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.
© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.