

ADDITOL[®] XL 123 N

TYPE

Flow agent and defoamer based on a modified silicone oil, for air drying and stoving coating systems

FORM OF DELIVERY (f.o.d.)

Active substance

approx. 50 %

Appearance

light yellow, clear, low viscous liquid

PRODUCT DATA

Determined per batch:

Iodine Colour Number DIN 6162

iodine colour number <= 5

Refractive Index DIN 53491

refractive index (20 °C) 1,4420 - 1,4500

Not continually determined:

Density (Liquids) DIN EN ISO 2811-2

density [g/cm³] approx. (20 °C) 0,85

Flash Point DIN EN ISO 1523

flash point [°C] approx. 31

SPECIAL PROPERTIES

Additol XL 123 N serves as additive in solventborne coating systems to increase slip, crack and scratch resistance and to improve flow. Further advantages are the foam breaking effect (without influence on recoatability) and the prevention of pigment flooding.

SUGGESTED USES

Additol XL 123 N prevents the formation of stable foam during manufacture and during application of the coatings. Defoaming is better in polar systems than in non-polar systems. No direct influence on intercoat adhesion and recoatability is observed when the recommended amounts of additive are used.

Additol XL 123 N is particularly effective in two-component polyurethane-coatings based on acrylate and alkyd resins and in stoving alkyd/melamine systems. It is effective in preventing foam formation in critical coating applications such as dipping, curtain coating and airless spraying.

PROCESSING

Additol XL 123 N can be added to the ready-to-apply paint. For fully effective defoaming it is advantageous to add Additol XL 123 N right at the beginning of paint manufacture.

The recommended amounts for use range between 0.05 - 0.5 % Additol XL 123 N, calculated on total paint.

On account of the large number of possible formulations, the optimum activity should be determined in preliminary trials.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

DISTINGUISHING FEATURES

Additol XL 123 N replaces Additol XL 123.

Due to its organic modification, Additol XL 123 N has a significantly stronger defoaming effect in critical systems than Additol XL 122.

6.0/30.03.2017 (replaces 5.0/17.09.2013)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.