

ADDITOL[®] XW 372 N

TYPE

High-efficiency defoamer for waterborne dispersions, interior and exterior emulsion paints

FORM OF DELIVERY (f.o.d.)

Active substance

100 %

SPECIAL PROPERTIES

Low foam processing of products.
 Stable against increased shear stress.
 Alkali-resistant up to pH = 13.
 Outstanding effectiveness at low amounts of addition.

PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219 dynamic viscosity (100 1/s; 23 °C)	[mPa.s]	50 - 250
--	---------	----------

Not continually determined:

Colour / Appearance VLN 250 colour appearance		pale yellow cloudy
---	--	-----------------------

Density (Liquids) DIN EN ISO 2811-2 density approx. (20 °C)	[g/cm ³]	0,88
--	----------------------	------

Flash Point (Pensky-Martens) DIN EN ISO 2719 flash point	[°C]	> 100
---	------	-------

SUGGESTED USES

Additol XW 372 N was developed specially for large to fine particle size dispersions based on polyvinyl acetate, PVC acrylates and their copolymers. With Additol XW 372 N, medium to low viscosity products can be defoamed and/or produced with low foam, e. g. disperions, emulsion paints and, after prior testing, high gloss paints for interior and exterior use based on:

- vinyl acetate and vinyl esters of carboxylic acids
- vinyl acetate/ethylene
- styrene und acrylic esters
- acrylic esters
- polyvinyl propionate etc. and copolymers thereof

- dispersion adhesives
- dispersion plasters
- glues
- polyvinyl alcohol solutions
- gloss plastics
- high gloss paints

The suitable and optimum amounts to be added should however be determined by a preliminary trial. Additol XW 372 N causes fully effective deaeration in unpigmented and pigmented systems, allows optimum milling conditions and shortens the mill time. Additol XW 372 N retains the effectiveness even with long-term storage of the end product. As well as in emulsion paints, this product can be used in other waterborne coating systems.

PROCESSING

Additol XW 372 N should be added in the mill batch. This guarantees a regular and optimum distribution in the system. Foam formation is prevented during the application of high shear rates. If necessary, Additol XW 372 N can be added at any stage of preparation.

After extended storage, phase separation may occur in the product. Therefore it is always good to shake or stir up the Additol XW 372 N before using.

We recommend 0.1 - 0.5 % Additol XW 372 N based on finished paint. A division of the amount to be added, i.e. half in the mill batch and half to the paint is advisable.

The amount to be added depends on the intensity of foaming and the composition of the foaming medium. In many dispersion systems the amount to be added can even be reduced to under 0.1 %. The optimum addition can be different for each individual formulation. In our tests overdoses of up to 1 % have shown no negative effects on the paint or coating system.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 365 days.

Phase separation is possible; however it can be eliminated by shaking up.

DISTINGUISHING FEATURES

Additol XW 372 N replaces Additol XW 372.

If FDA approval is required, Additol VXW 6381 should be used.

6.0/30.03.2017 (replaces 5.0/17.09.2013)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.