

### INTRODUCTION

SETALUX 17-1275 is a fast-dry thermoplastic acrylic resin solution supplied in Aromatic 100. This resin solution may be utilized in various clear or pigmented air-dry or force-dry general industrial finish coats. The dry speed, compatibility, durability and non-yellowing characteristics of SETALUX 17-1275 make it a very suitable choice for use in a broad range of coatings.

### TYPE

Thermoplastic acrylic resins solution

### FORM OF DELIVERY (F.O.D)

45% non-volatile in aromatic 100

### PRODUCT DATA

Non-Volatile, by wt:	51.0 ± 1.0 %
Viscosity (77° F):	Z4 – Z6 Gardner Holdt
Acid value, on n.v.:	6 maximum mg KOH/g
Color:	125 maximum APHA
Appearance:	clean, clear and free from extraneous matter
Density:	8.25 ± 0.10 lbs/gal
Flash Point:	113° F Setaflash
Non-volatile, by vol:	44.4%
Reduced viscosity:	Y – Z2 Gardner – Holdt @ 45% in aromatic 100

### PERFORMANCE HIGHLIGHTS

- Excellent general purpose fast air-dry or force-dry resin for industrial or refinish use
- May be utilized for clear or pigmented coatings

### SUGGESTED USES

- Durable, non-yellowing resin for general coatings and refinish usage
- Very well suited for fast-dry, durable aerosol coatings
- Ideal for use with Setyrene 13-3504 type acrylic modified alkyds

### STORAGE

At temperatures up to 100°F storage stability packed in original containers amounts for 3 years.

### PRECAUTIONS

Before using SETALUX 17-1275, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

### STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation. See the SDS for the recommended storage temperature range for SETALUX 17-1275.