

PHENODUR® PR 516/60B

TYPE

Curable, unplasticized phenolic resin

FORM OF DELIVERY (f.o.d.)

60 % in butanol (60B)

USES

In combinations with epoxide resins excellent adhesion, hardness and flexibility. Very good resistance against chemicals, mineral oils and food. Coatings based on Phenodur PR 516 are preferably used for the interior coating of metal packaging goods.

PRODUCT DATA

Determined per batch:

Dynamic Viscosity (Ubbelohde) DIN 53177		
dynamic viscosity	[mPa.s]	150 - 500
(23 °C)		

Non-Volatile Matter DIN EN ISO 3251		
non-volatile matter	[%]	58 - 62
(1 h; 135 °C; 2 g; B)		

Iodine Colour Number DIN 6162		
iodine colour number		<=150

Not continually determined:

Density (Liquids) DIN EN ISO 2811-2		
density	[g/cm³]	1,03
approx.		
(20 °C)		

Flash Point DIN EN ISO 1523		
flash point	[°C]	30
approx.		

DILUTABILITY AND COMPATIBILITY

Phenodur PR 516 is unlimited diluteable with alcohols, esters and ketones. Phenodur PR 516 is limited diluteable with aromatic and aliphatic hydrocarbons. PR 516 is compatible with high molecular weight epoxide resins and poly vinyl butyral.

PROPERTIES AND USES

Phenodur PR 516 has been preferably developed to be combined with high molecular weight epoxide resins, e.g. Beckopox EP 304, EP 307 and EP 309. Such combinations are suitable to formulate transparent, heat curing coatings for the interior coating of metal packaging goods like collapsible tubes, cans and containers for water, oils and food. Such coatings resist to a great variety of acids, alkalines, organic solvents and food.

PROCESSING

Phenodur PR 516 combinations with high molecular weight epoxide resins have to be stoved for 10 - 20 min. at 190 - 210 °C to be fully cured. Acidic catalysts, like Additol XK 406 (in amounts of 2 - 5 %, calculated on solid resin), may be used to reduce the temperature to 180 - 200 °C and may improve adhesion and hardness. In multiple layer coatings, the first coats are not subjected to the full cure, the coating system as a whole is completely cured only after the last coat has been applied. In case of surface defects, more likely with catalysed systems, the addition of approximately 1 - 3 % of a melamine resin like Maprenal MF 800 acts as an excellent flow agent. A precondensation between the phenolic and the epoxide resin at approximately 100 °C (under reflux) also improves the flow of the finished coating. The mixing ratio between Phenodur PR 516 and the epoxide resin should be between 1 : 2 and 1 : 4 (calculated as solid resins). The light colour of the cured film can be tinted with a coloring resin like Phenodur PR 308, towards a "gold lacquer".

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 365 days.

DISTINGUISHING FEATURES

Phenodur PR 516 is more reactive and lighter in colour than Phenodur PR 217, PR 722, PR 723 and PR 897. Phenodur PR 516 is comparable with Phenodur PR 515 but does not contain Bisphenol A as monomer.

4.0/30.03.2017 (replaces 3.0/17.09.2013)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.
© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.