

DAOTAN[®] VTW 1265/36WA

TYPE

Aqueous, solvent-free self crosslinking polyurethane dispersion

Neutralization agent

approx. 0.9 % N,N-dimethylethanolamine, as salt

FORM OF DELIVERY (f.o.d.)

36 % in water (36WA)

PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219 dynamic viscosity (100 1/s; 23 °C)	[mPa.s]	10 - 90
--	---------	---------

pH-Value DIN ISO 976 pH-value		7,0 - 8,0
----------------------------------	--	-----------

Non-Volatile Matter DIN EN ISO 3251 non-volatile matter (1 h; 125 °C; 1 g)	[%]	35 - 37
--	-----	---------

Not continually determined:

Colour / Appearance VLN 250 colour appearance		pale yellow translucent
---	--	----------------------------

Density (Liquids) DIN EN ISO 2811-2 density approx. (20 °C)	[g/cm ³]	1,05
--	----------------------	------

Flash Point (Pensky-Martens) DIN EN ISO 2719 flash point	[°C]	> 100
---	------	-------

SPECIAL PROPERTIES AND USE

Daotan VTW 1265 is a solvent-free polyurethane dispersion with excellent wetting properties, which yields without coalescing agents, crack-free films on drying.

Due its high brilliance Daotan VTW 1265 is suitable for the formulation of aqueous wood coatings (furniture and parquet). By blending with acrylic emulsions drying can be accelerated.

Due to excellent adhesion properties on several plastic grades, e. g. ABS, PA, PC and PMMA, Daotan VTW 1265 can be preferably used for plastic coatings. The adhesion to any plastic substrate to be coated should first be carefully examined.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 365 days.

It is important to protect Daotan VTW 1265 from frost; at low temperatures it has therefore to be stored under frostproof conditions.

Because of the amphiphilic character of Daotan VTW 1265 the product tends to foam. Caused by the selfcrosslinking moieties of the product, these foams can establish unreemulsifiable films, also in closed containers. We strongly recommend to filtrate the product with a 5 µm filter before use.

5.0/17.07.2013 (replaces all previous versions)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies (*Allnex*) decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.