


LONGSORB 27



ITEM

SPECIFICATION

Molecular Weight:	357.9	
Appearance :	Slightly yellow powder	
Specific gravity :	Approx. 1.26 @ 20 °C	
Volatility :	0.5 % Max.	
Transmittance : (10 g in 100 ml toluene : 1 cm cell)	460 nm 500 nm	97 % Min. 98 % Min.
Assay :	98.0 % Min.	
Packing :	25 KGS / DRUM, 125KGS / PALLET	
Application :	LONGSORB 27 is mainly used as UV absorber for styrene polymers PVC, unsaturated polyesters, PU, acrylic polymers, polycarbonate adhesives and coating.	

Notice: Above information is based on our own investigation and experience, we do not assume any responsibility for the performance or result obtained through the use of our product. The users need to check the quality, safety and all properties in their side before they use and commercialize their products. Neither Longchem nor our agents shall take any responsibilities for any injury, loss or damages directly or indirectly caused by our products.

Longchem C & S International Corp.

12FL , 80 , Fu Hsing N. Road
Taipei , Taiwan , R.O.C.
P.O. Box. 34-167 Taipei , Taiwan

Tel : 886-2-27718177
Fax : 886-2-27788748