

Continuing a Legacy of  
Customer Focus and Innovation  
functional anhydrous and hydrous aluminum silicates

*Burgess Pigment*

## BURGESS NO. 60

### HYDROUS ALUMINUM SILICATE

**BURGESS NO. 60** is an acid pH, fine particle size, medium brightness hydrous kaolin clay with excellent dispersion properties.

**BURGESS NO. 60** is used in inks, adhesives and industrial finishes, electrostatic deposition body primers, and EIFS.

Typical Physical Properties		Typical Chemical Properties	
GE Brightness %	86.0	Loss On Ignition %	13.7 – 14.1
325 Mesh Residue %	0.01	Silica (SiO <sub>2</sub> ) %	44.8 – 45.3
Average Particle Size Sedigraph	0.4 μ	Alumina (Al <sub>2</sub> O <sub>3</sub> ) %	37.5 – 39.7
Free Moisture %	1.0	Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> ) %	Trace
Specific Gravity	2.63	Titanium Dioxide (TiO <sub>2</sub> ) %	1.35 – 2.27
Refractive Index	1.56		
pH (20% Solids)	4.7		

Issue Date: HD00F

The suggestions and data contained in this bulletin are based on data which are believed to be reliable. They are offered in good faith, to be applied according to the user's own best judgment. Since operating conditions in the processor's plant are beyond our control, Burgess Pigment Company cannot assume responsibility for any risks or liabilities which may result from the use of its products. Likewise, no liability is assumed for any claimed patent infringement occurring by reason of any method or manner of use, or any product made by a consumer. While the Burgess Pigment Company guarantees the quality of its products, it cannot give any warranty regarding the results obtained by the use thereof.