

RHEOTECH™ 2800

Acrylic associative thickener for water-based systems

HASE Acrylic Thickener

TYPICAL CHARACTERISTICS

Nature	Aqueous dispersion of an acrylic copolymer
Appearance	Low viscous white milky liquid
Solid Content (%)	30
Active Content (%)	30
pH	3
Specific gravity	1.06
Solvent	Water

DESCRIPTION

Rheotech™ 2800 is an associative acrylic thickener providing a newtonian to balanced rheology profile.
Rheotech™ 2800 is part of the Rheotech™ x800 new thickener range

STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC
- 200L Drum
- Bulk

HANDLING & STORAGE

It can be irreversibly altered by frost. It should be protected from the effects of weathering and stored between 5 and 40°C and protected from direct sun exposure.

Once opened, packaging should be resealed immediately after use.

Film-forming product, surface may dry in contact with air.

A slight sedimentation can be visible at the bottom of drums or totes. This phenomenon is normal and has no impact on the use and level of performance as long as the solids content of the product meets the specification. If necessary, filter the product prior to its use.

In these conditions, this product should be used within 6 months from delivery.

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

MARKET

Coatings & Inks

- Architectural Coating
- Graphic Arts
- Industrial Coating
- Textile & Leather Coating

KEY BENEFITS

FORMULATION

- **Color acceptance**
- **Cost in use**
- **Compatibility**



STORAGE

- **In-can appearance**
- **Syneresis resistance**
- **Antisettling**
- **Viscosity stability**



APPLICATION

- **Spatter resistance**
- **Tinting resistance**
- **Dilution resistance**



FILM PROPERTIES

- **Hiding power/Opacity**
- **Rub out**
- **Stain resistance**



- **APEO free** Yes
- **Bacteria resistance** Yes
- **Heavy metal free** Yes
- **Solvent-free** Yes

THICKENING MECHANISM

Associative
Non Associative
Self Association

VISCOSITY CONTRIBUTION

High Shear contribution
Low Shear contribution
Mid Shear contribution

PVC

PVC High
PVC Mid
PVC Low